



E-ISSN: 2278-4136
P-ISSN: 2349-8234
JPP 2018; SP5: 96-99

Bhupinderjeet Singh
COAE & T, PAU Ludhiana,
Punjab, India

Ritesh Jain
COAE & T, PAU Ludhiana,
Punjab, India

(Special Issue- 5)

Advances in Agriculture and Natural Sciences for Sustainable Agriculture (October 12 &13, 2018)

Use of waste glass in concrete: A review

Bhupinderjeet Singh and Ritesh Jain

Abstract

Concrete is widely used construction material in the present industry. The concrete consists of cement, fine aggregates and coarse aggregates. Concrete is strong in compression and weak in tension. Also the cement manufacturing industry on an average emits 7% of greenhouse gases to earth's atmosphere which leads to global warming. In order to address these environmental affects extensive research is on going into the use of cement replacements, using many waste materials [like waste glass, plastics, fly ash, etc.] and industry's byproducts. Waste glass is a non- biodegradable material and disposal of waste glass into the land results in the soil pollution. So to avoid these disposable problems waste glass may be used as partial replacements of coarse and fine aggregates. It's possible to add glass in the concrete by replacing either of the ingredients partially in a number of forms. Glass may be added in crushed form or in powder form along with the addition of admixtures/plasticizers or without addition of any of the alternate materials in the nominal concrete. Accordingly, a study about various aspects of usage of glass has been made in this paper to include it in concrete as an ingredient so that the best possible usage of glass form may be finalized and same may be used in the concrete with a partial replacement.

Keywords: Waste Materials, Glass Powder, Concrete, Admixtures

Introduction

Concrete is widely used construction material in the present industry. The concrete consists of cement, fine aggregates and coarse aggregates. Concrete is strong in compression and weak in tension. Also the cement manufacturing industry on an average emits 7% of greenhouse gases to earth's atmosphere which leads to global warming. In order to address these environmental affects extensive research is ongoing into the use of cement replacements, using many waste materials [like waste glass, plastics, flyash, etc.] and industry's byproducts. Waste glass is a non- biodegradable material and disposal of waste glass into the land results in the soil pollution. So to avoid these disposable problems waste glass is used as partial replacements of coarse and fine aggregates. Use of waste glass in concrete makes the structure denser, this results in reduction of water absorption and improves durability of concrete. The addition of glass powder in concrete shows improvement in the compressive strength, flexural strength and tensile strength. It's possible to add glass in the concrete by replacing either of the ingredients partially in a number of forms. Glass may be added in crushed form or in powder form along with the addition of admixtures/plasticizers or without addition of any of the alternate materials in the nominal concrete. Accordingly the present study has been planned under following sub headings:

- Use of waste glass powder as a replacement in concrete
- Use of waste glass as partial replacement in concrete
- Use of glass powder and aggregates as partial replacement in concrete.

Use of Waste Glass Powder as a Replacement in Concrete

Vijay kumar *et al.* (2013) ^[19] examined that worldwide concrete industry contributes around 7% of ozone depletion gases to the earth's atmosphere. So in this research finely glass powder was used as partial replacement of cement for new concrete. Glass powder was mostly replaced as 10%, 20%, 30%, 40% and tried for its compressive strength, tensile strength and flexural quality upto 60 days of curing age and results obtained were compared with those of regular cement. From the results it is discovered that glass powder can be utilized as substitute

Correspondence
Bhupinderjeet Singh
COAE & T, PAU Ludhiana,
Punjab, India

material upto molecule size less than 75 μm to avoid salt silica reaction. It was also concluded that with increase in glass powder content upto 40% it's compressive strength increases further increase in glass powder leads to decrease in its compressive strength.

Vasudevan and Kanapathy Pillay *et al.* (2013) ^[18] did their research on examining the impact of utilizing the waste glass powder in concrete. The properties of the specimens were determined by the workability test, density test, and compressive strength test. For each kind of concrete, six samples of 150mm x 150mm x 150mm cubes were casted. The each sample were tried at the ages of 7, 14, and 28 days to find the advancement in the compressive strength of concrete. The outcomes from the experiment showed that the solid with glass powder could expand the workability and compressive strength of the concrete.

Bhagyasri *et al.* (2016) ^[3] carried out a research in which cement was partially replaced by 90 μm glass powder in concrete. As glass powder exhibit pozzolana properties so it was utilized as a partial substitution of cement in concrete. To study different mechanical properties for example compressive strength, flexural quality and Modulus of elasticity of concrete with part of glass powder in the concrete. Different specimens were casted using M20 grade concrete resolved with various percentages of glass powder i.e. 0%, 10%, 20%, 30% and 40%. The specimens were tested at different age of 7days and 28 days. The results of the test conducted in the laboratory showed that the maximum compressive was observed at 20% of glass powder in concrete. Additionally quality of the cement was tested by the UPV test. The outcomes show that the solid with utilizing waste glass powder could enhance the strength and quality of cement.

Jangid and Saoji *et al.* (2014) ^[8] did a research work on replacing the cement with waste glass powder which act as a filler material instead of cement which takes some part in response to the reaction at the time of hydration. When waste glass was brought to fine powder it starts exhibiting pozzolanic properties as it contains SiO_2 and accordingly upto some extent glass powder can be utilized in concrete and contribute quality improvement. In the test Glass powder was added to the specimens at different rate from 0 to 40%, at the interim of 5% and examined for its compressive, tensile and flexural strength upto 60 days and were contrasted with those of regular cement. From the results it was concluded that maximum strength was acquired when 20% concrete was replaced by waste glass powder.

Use of Waste Glass as Partial Replacement in Concrete

Malik *et al.* (2013) ^[13] addressed the issues of ecological and financial challenges faced by the cement industry by utilizing waste glass as partial substitution of fine aggregates in concrete. Various samples were prepared with different concentration of glass as 10%, 20%, 30% and 40% by weight in the M-25 grade concrete. The samples were tested for compressibility strength, splitting tensile strength and density at 28 days of curing age. The outcomes from the result were compared with the normal concrete. The specimens with the glass showed better results in terms of compressive strength upto 30% replacement of fine aggregates by weight for particle size of 0.1-1.18 mm. The specimens with glass content also proved to be more economical and environment friendly.

Ramana and Samdani *et al.* (2013) ^[14] studied the effects of replacing fine aggregates of sand with waste glass in the

extents of 0%, 5%, 10%, 15%, 20%, 25% and 30%. Different mechanical properties like compressive strength, split tensile strength and flexural strength were surveyed in this paper. The results obtained from the laboratory tests were noted and compared with the conventional concrete. It was observed from the results that upto 15% replacement of fine aggregates by crushed glass there was increase in the mechanical properties and decreases as fine aggregates replacement by crushed glass reaches upto 30%.

Dabiri *et al.* (2018) ^[4] carried out this study to find the impacts on the compressive strength and moreover the effects on the weight of the concrete by substituting the concrete aggregates with waste glass particle. To accomplish the objective 27 cubic specimens were made; out of which 6 specimens were made of normal concrete, while in the rest of the specimens glass particles were mixed in different proportions. Micro-silica was added to the cubes containing glass to suppress the Alkali Silica reaction (ASR). From the test results it was demonstrated that replacing aggregates with glass particles over 30% leads to increase in the compressive strength. The weight of the concrete remains nearly same for majority of the samples. From the outcomes it could be concluded that the ideal proportion for replacing aggregates with glass particle is 50%.

Ganiron Jr. *et al.* (2014) ^[6] conducted this experimental study in order to find the alternative for replacing coarse aggregates in the concrete mixture. In this study crushed glass bottles were utilized at the place of coarse aggregates and its impact on the physical and mechanical properties of the mixture were noted. The experimental outcomes showed that optimum replacement of coarse aggregates with recycled glass bottles is upto 10% weight of coarse aggregates and a mixture design of 5% weight addition to the concrete mix provide the desirable results for compressive strengths. Through the experiment it was proved that coarse aggregates can be effectively replaced by the recycled glass bottles.

Turgut and Yahlizde (2009) ^[17] conducted their experimental study by replacing the Fine Aggregates (FA) of concrete mixture by various levels of Fine glass (FG) and Coarse Glass (CG) and researching the physical and mechanical properties of the cubes. The results from the FG and CG replacement were compared to each other. The values of various properties like compressive strength, flexural strength, splitting tensile strength and abrasion resistance of the samples were observed and noted at 20% FG replacement. Their values were 69%, 90%, 47% and 15% more in comparison to the normal concrete sample. From the results it was also concluded that at 20% replacement level by weight of FG suppresses the alkali-silica reaction (ASR) in the concrete.

Kavyateja *et al.* (2016) ^[10] did their study on examining the replacement of fine particles by the squashed glass. The control mixing proportion of 1:1.5:3 grouped by volume with water bond proportion of 0.5. The samples were prepared with substitution rate varied from 0% to 40% at a interval of 10%. To analyze the compressive characteristics of concrete samples of sizes 150mm x 150mm x 150mm were casted and examined at 3days, 7 days, 28 days, 56days and 90 days. From the experimental results it was found that the compressive strength increases up to 20% substitution level and at 30%, 40% substitution level it goes on decreasing. From split tensile strength test it was also concluded that Split tensile strength goes on decreasing with increasing glass content.

Elaiyarasu *et al.* (2015) ^[5] did a research work on investigating the effects on strength of concrete when recycles

glass bottles were used as an alternative coarse aggregate. From the test results it was proved that glass replaced aggregates shows better results in strength and more economical than conventional concrete.

Use of Glass Powder and Aggregates as Partial Replacement in Concrete

Tang *et al.* (2016) ^[15] carried out their research with aim to use recycled concrete aggregates (RCA) in Self Compacting Concrete (SCC) which possibly decrease both the natural effect and economical cost of concrete. The work introduced in this paper examines the quality, strength and break properties of SCC's containing RCA content from 0% to 100% at an interim of 25%. The test results showed that at RCA use levels of 25% to 50% have very little or no negative effect on the strength, workability, and breakage properties. Except for slight decrease in the young's modulus. With further increase in RCA content beyond 50% its fracture energy decreases.

Yahia *et al.* (2017) ^[20] conducted an experimental study on the use of fly ash and waste glass powders as a partial replacement in the concrete to test the enhancement in the workability and strength of the concrete. In this experiment material from Jaresh city was utilized. Based on the laboratory tests they concluded that by adding 10% fly ash or waste glass results in a significant increase in the compressive strength and workability of the concrete and addition of fly ash or waste glass content by more than 20% leads to decrease in the compressive strength of concrete.

Kou and Poon, (2008) ^[11] did their research on studying the impacts of using recycled glass (RG) cullet on the properties of self-compacting concrete (SCC). RG was utilized as replacement for the sand in the extents of 10%, 20%, and 30% and adding 10mm granite powder (5%, 10% and 15%) in casting of the SCC concrete mixes. From the experimental results it was concluded that the properties like slump flow, blocking ratio, air content of the RG-SCC mixes increases with increasing Recycled glass content upto certain limit after passing the limit properties like compressive strength, tensile splitting strength and static modulus of elasticity starts decreasing. The outcomes demonstrated that it is possible to use SCC with Recycled Glass cullet.

Tariq *et al.* (2016) ^[16] investigated the effects of alteration of the superplasticizer (SP) in Self-compacting concrete (SCC) mixture containing waste glass powder of varying sizes as concrete substitutes. To examine the variation three glass measure ranges [10 μ m, 20 μ m and 40 μ m] were analyzed. The experimental results indicated that the finer glass is affected more by the SP dosage in contrast to the coarser glass. With increasing SP dosage compressive strength also increases upto certain level further increase in SP dosage leads to strength loss due to microstructural damage. 10 μ m glass substituted at a 30% substitution rate gave the most comparable results to Class F Fly ash concrete.

Lavanya and Karuppasamy, (2016) ^[12] used the glass powder and granite powder in the concrete. The strength of the concrete was analyzed and compared with the normal concrete after curing period of 7, 14 and 28 days. The M20, M30, and M40 grade concrete was utilized for this experimental purpose. Through the experimental results it was concluded that glass powder and granite powder can be utilized as an alternate material in the concrete reducing the cement consumption and cost of construction as compared to conventional concrete. The maximum compressive strength was obtained at replacement level of 20% for Glass powder

and 25% of Granite powder in all grades of concrete.

Batayneh *et al.* (2006) ^[2] carried out the research on substituting the recycled waste materials in the ordinary Portland cement concrete (OPC). The waste Materials reused in this examination comprises of glass, plastics, and demolished concrete. Ground plastics and Glass were utilized to substitute the 20% of fine aggregates in concrete mixture while demolished concrete was utilized to substitute 20% of coarse particles of the concrete. To assess these substitutions and their impacts on OPC mixture various tests were conducted. These tests included workability, unit weight, and compressive strength, flexural and indirect tensile strength. The fundamental discoveries of this research uncovered that the three kinds of waste materials can be reused effectively as substitutes for sand and coarse aggregates in concrete mixture.

Conclusion

From the study of work presented in the various papers, it was observed that waste glass, glass powder and glass powder with aggregates can be successfully utilized in the partial replacements of fine and coarse aggregates in the concrete. Out of the three replacement in the ingredients of the concrete, glass powder was found to be most suitable for the structural applications. The results demonstrated that utilization of glass powder might increase the compressive strength, flexural strength, workability and tensile strength of the concrete. The maximum compressive strength may be obtained at 20% replacements of fine aggregates with glass powder. Moreover the concrete containing glass powder will also prove to be economical and environment friendly as compared to conventional concrete. So a detailed study will be undertaken in the nominal concrete with the glass powder as partial replacement.

References

1. Al-Bawi RK, Kadhim IT, Al-Kerttani O. "Strengths and Failure Characteristics of Self-Compacting Concrete Containing Recycled Waste Glass Aggregate". *Advances in Materials Science and Engineering*, 2017, 12.
2. Batayneh M, Marie I, Asi I. "Use of Selected waste materials in Concrete mixes". *Waste Management*. 2017; 27:1870-76.
3. Bhagyasri T, Prabhavathi U, Vidya N. "Role of Glass Powder in Mechanical Strength of Concrete". *International Journal of Advances in Mechanical and Civil Engineering*. 2016; 3:74-78.
4. Dabiri H, Sharbatdar MK, Kavyani A, Baghdadi M. "The Influence of Replacing Sand with Waste Glass Particle on the Physical and Mechanical Parameters of Concrete". *Civil Engineering Journal*. 2018; 4:1646-52
5. Elaiyarasu S, Dhaarani M, Jagateesh P. "Experimental Investigation on Concrete with Partial Replacements of Waste Glass as Coarse Aggregates". *International Journal of Innovative Research in Science, Engineering and Technology*. 2015; 4:138-143
6. Ganiron TU. "The Effect of Waste Glass Bottles as an Alternative Coarse Aggregates in Concrete Mixture". *International Journal of ICT-aided Architecture and Civil Engineering*. 2014; 02:1-10.
7. Gumede MT, Franklin SO. "Studies on Strength and Related Properties of Concrete Incorporating Aggregates From Demolished Wastes: Part 2- Compressive and Flexural Strengths". *Open Journal of Civil Engineering*. 2015; 5:175-84
8. Jangid JB, Saoji AC. "Experimental Investigation of

- Waste Glass Powder as The partial replacements of Cement in Concrete Production”. *IOSR Journal of Mechanical and Civil Engineering*, 2014, 55-60.
9. Junior EJPDM, Bezerra HDJCL, Politi FS, Paiva AEM. “Increasing the Compressive Strength of Portland Cement Using Flat Glass Powder”. *Material Research*. 2014; 17:45-50.
 10. Kavyateja BV, Reddy PN, Mohan UV. “Study of Strength Characteristics of Crushed Glass used as Fine Aggregates in Concrete”. *International Journal of Research in Engineering and Technology*. 2016; 05:157-160
 11. Kou SC, Poon CS. “Properties of Self Compacting Concrete Prepared with Recycled Glass Aggregates”. *Cement and Concrete Composites*, 2009, 107-113.
 12. Lavanya G, Karrupasamy R. “Experimental Study on Concrete Using Glass Powder and Granite Powder”. *International Journal of Advanced Engineering Research and Technology*. 2016; 4:97-101.
 13. Malik MI, Bashir M, Ahmad S, Taruq T, Chowdhary U. “Study Of Concrete Involving Use of Waste Glass as Partial Replacement of Fine Aggregates”. *International Organization of Scientific Research Journal of Engineering*. 2013; 3:08-13.
 14. Ramana KV, Samdani SS. “Study on Influence of Crushed Waste Glass on Properties of Concrete”. *International Journal of Science and Research*. 2013; 4:1034-39.
 15. Tang WC, Ryan PC, Cui PC, Liao W. “Properties of Self-Compacting Concrete with Recycled Coarse Aggregates”. *Advances in Material Science and Engineering*. 2016, 1-11.
 16. Tariq SA, Scott AN, Mackechnie JR. “Controlling Fresh Properties of Self-Compacting Concrete Containig Waste Glass Powder and Its Influence On Strength and Permeability”. *Sustainable Construction Materials and Technologies*, 2016, 10.
 17. Turgut P, Yahlizade ES. “Research into Concrete Blocks with Waste Glass”. *International Journal of Civil and Environmental Engineering*. 2009; 3(3):186-92
 18. Vasudevan G, Pillay SGK. “Performance of Using Waste Glass Powder in Concrete as Replacement of Concrete”. *American Journal of Engineering Research*, 2013.
 19. Vijayakumar G, Vishaliny H, Govindarajulu D. “Studies on Glass Powder as Partial Replacement of Cement in Concrete production”. *International Journal of Emerging Technology and Advanced Engineering*. 2013; 3:153-57.
 20. Yahia YIO, Alsharie H, Suliman MO, Masoud T. “Effects of Wood Ash and Waste Glass Powder on properties of concrete in Terms of Workability and Compressive Strength in Jareh City”. *Open Journal of Civil Engineering*. 2017; 7:423-31.